

959

Low-Solids No-Clean Liquid Flux

Product Description

Kester 959 is a no-clean, non-corrosive, halogen free liquid flux that is designed for the wave soldering of conventional and surface mount circuit board assemblies. Kester 959 was developed to minimize the formation of micro-solderballs during wave soldering operations. This flux contains a small percentage of rosin (1%), which improves solderability, heat stability and surface insulation resistance. Kester 959 offers the best wetting and the shiniest solder joints of any no-clean, solvent-based chemistry. Kester 959 leaves evenly distributed residues for the best cosmetic appearance.

Performance Characteristics:

- Minimize micro-solderballs
- Extremely shiny joints
- No streaky, white residues
- Improves soldering performance
- Eliminates the need and expense of cleaning
- Classified as ORL0 per J-STD-004
- Compliant to Bellcore GR-78

Physical Properties

Specific Gravity: 0.810 ± 0.005

Antoine Paar DMA 35 @ 25°C

Percent Solids (typical): 3.9

Tested to J-STD-004, IPC-TM-650, Method 2.3.34

Acid Number: 21.8 ± 1.5 mg KOH/g of flux

Tested to J-STD-004, IPC-TM-650, Method 2.3.13

pH (10% solution): 4.6

Hanna Instruments 8314 @ 25°C

Flash Point: 18°C (64°F)

Reliability Properties

Copper Mirror Corrosion: Low

Tested to J-STD-004, IPC-TM-650, Method 2.3.32

Corrosion Test: Low

Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Silver Chromate: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.33

Chloride and Bromides: None Detected

Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass

Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

SIR, IPC (typical): Pass

Tested to J-STD-004, IPC-TM-650, Method 2.6.3.3

	Blank	959 PD	959 PU
Day 1	$2.7 \times 10^{10} \Omega$	$2.4 \times 10^{10} \Omega$	$2.4 \times 10^{10} \Omega$
Day 4	$1.5 \times 10^{10} \Omega$	$1.5 \times 10^{10} \Omega$	$1.4 \times 10^{10} \Omega$
Day 7	$1.2 \times 10^{10} \Omega$	$1.2 \times 10^{10} \Omega$	$1.1 \times 10^{10} \Omega$

Application Notes

Flux Application:

Kester 959 can be applied to circuit boards by a spray, foam or dip process. Flux deposition should be 120-240 µg of solids/cm² (750-1500 µg of solids/in²). An air knife after the flux tank is recommended to remove excess flux from the circuit board and prevent dripping on the preheater surface.

Process Considerations:

The optimum preheat temperature for most circuit assemblies is 90-105°C (194-221°F) as measured on the top or component side of the printed circuit board. Dwell time in the wave is typically 2-4 seconds. The wave soldering speed should be adjusted to accomplish proper preheating and evaporate excess solvent, which could cause spattering. For best results, speeds of 1.1-1.8 m/min (3½-6 ft/min) are used. The surface tension has been adjusted to help the flux form a thin film on the board surface allowing rapid solvent evaporation.

Flux Control:

Acid number is normally the most reliable method to control the flux concentration of low solids, no clean fluxes. To check concentration, a simple acid-base titration should be used. PS-22 Test Kit and procedure are available from Kester. Control of the flux in the foam flux tank during use is necessary for assurance of consistent flux distribution on the circuit boards. The complex nature of the solvent system for the flux makes it imperative that Kester 4662-SM Thinner be used to replace evaporative losses. When excessive debris from circuit boards, such as board fibers and from the air line build up in the flux tank, these particulates will redeposit on the circuit boards which may create a build up of residues on probe test pins. It is, therefore, necessary to clean the tank and then replenish it with fresh flux when excessive debris accumulates in the flux tank.

Cleaning:

Kester 959 flux residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, call Kester Technical Support.

Storage and Shelf Life:

Kester 959 is flammable. Store away from sources of ignition. Shelf life is 2 years from date of manufacture when handled properly and held at 10-25°C (50-77°F).

Health & Safety:

This product, during handling or use, may be hazardous to health or the environment. Read the Material Safety Data Sheet and warning label before using this product.

World Headquarters: 515 E. Touhy Avenue, Des Plaines, Illinois, 60018 USA
Phone: (+1) 847-297-1600 • **Email:** customerservice@kester.com • **Website:** www.kester.com

Asia Pacific Headquarters
 500 Chai Chee Lane
 Singapore 469024
 (+65) 6449-1133
 customerservice@kester.com.sg

European Headquarters
 Ganghoferstrasse 45
 D-82216 Gernlinden
 Germany
 (+49) 8142-47850
 customerservice@kester-eu.com

Japanese Headquarters
 20-11 Yokokawa 2-Chome
 Sumida-Ku
 Tokyo 130-0003 Japan
 (+81) 3-3624-5351
 jpsales@kester.com.sg

The data recommendations presented are based on tests, which we consider reliable. Because Kester has no control over the conditions of use, we disclaim any responsibility connected with the use of any of our products or the information presented. We advise that all chemical products be used only by or under the direction of technically qualified personnel who are aware of the potential hazards involved and the necessity for reasonable care in their handling. The technical information contained herein is consistent with the properties of this material but should not be used in the preparation of specifications as it is intended for reference only. For assistance in preparing specifications, please contact your local Kester office for details.

Rev: 06Aug04